

## PRODUCT DATA SHEET FOR EPDM SETTING BLOCKS

S. No.	Characteristics Tested	Standard Followed	Typical Results
1.	Hardness (Shore A)	ASTM-D2240	85 <sup>0</sup> (+/-5 <sup>0</sup> )
2.	Tensile Strength (Kgf/cm <sup>2</sup> )	ASTM-D412	> 85
3.	Elongation at Break (%age)	ASTM-D412	> 220
4.	Tear Strength (Kgf/cm)	ASTM-D624	-
5.	Specific Gravity	ISO-2781	1.25
6.	Compression Set (max. %)  At 70 <sup>0</sup> for 22 Hrs.	ASTM-D395	28
7.	AGE RESISTANCE	ASTM-D573	
	a. <i>Hardness</i>		+8
	b. <i>Tensile Strength (%)</i>		+10
	c. <i>Elongation at Break (%)</i>		-20
8.	Ozone Resistance	ASTM-D1149	No visible Cracks